

Factsheet

Thermafleece CosyWool Slab is a versatile flexible insulation rich in British sheep's wool and is the ideal choice if you are looking for all round performance and value for money.

Research shows that using 75% wool in combination with recycled fibres outperforms alternative products with a higher percentage of wool. Our wool rich blend ensures you get the full benefit of sheep's wool with enhanced performance, durability and sustainability.

CosyWool Slabs are flexible but denser than rolls and provide friction fit in walls and roofs providing excellent thermal and acoustic performance.

Like all Thermafleece products, it is long-lasting, safe to handle and contributes to a healthier indoor environment by regulating moisture and absorbing harmful airborne substances in the home.

Key Information

-  Width (mm) – 350, 370
-  Vapour open
-  Thickness (mm) – 50, 75, 100, 140
-  Thermal conductivity – 0.038 W/mK
-  Sound absorption – NRC 1.05 @ 100mm
-  Recyclable
-  Manufactured to ISO 9001 & 14001
-  Made in the UK
-  Made from British wool
-  Contains recycled materials – 25%
-  Highly breathable

Best For

- Floors – All levels above Damp-Proof Course
- Lofts – Cold roofs
- Warm Roofs – Pitched roof or attic conversions
- Walls – Timber frame & solid (internal)

Why Insulate with Thermafleece CosyWool Slab?

Insulating a property will significantly reduce the amount of energy lost from the building envelope,

reducing energy consumption and carbon dioxide released to the atmosphere.

Affordable

Thermafleece CosyWool Slab is designed to minimise up-front cost making wool-based insulation more affordable to a wide range of end users. What's more, the energy it saves means Thermafleece CosyWool Slab quickly pays for itself.

Long Lasting

Thermafleece CosyWool Slab contains a lofting agent to maintain durability, fibre stability and structural integrity creating a long-lasting insulation.

Quality Assured

Thermafleece CosyWool Slab is manufactured and supplied in accordance with ISO 9001 quality management systems.

Sustainable

Thermafleece CosyWool Slab can reduce CO₂ emissions by many tonnes over the lifetime of use. What's more, wool fixes carbon dioxide helping reduce greenhouse gas levels.

Breathable

Insulating with breathable natural fibres can contribute to more stable humidity and moisture levels within buildings. This can help improve the health of the building and the occupants.

Safe

Thermafleece CosyWool Slab is safe to handle and can be recycled or safely disposed of at the end of its life.

Technical Support

We offer a comprehensive support to meet all your technical requirements including:

- For technical advice call **01768 486285**
- On-site and off-site support throughout the design and build process
- Advice on meeting current regulations including Building Regulations
- U-value and condensation risk analysis
- Advice on environmental impact
- Application guidance notes, comprehensive product data and reports

Specifications

Performance

- Dimensional Stability to EN 1604 – Pass
- EPD registration no. S-P-04468

- EPD valid to 31/10/26
- Fire Classification – EuroClass E
- Flammability & Smoulder Resistance (BS 5803-4) - Pass
- Manufactured to ISO 9001 & 14001
- Moth/Beetle Proofing: ISO 3998 - Pass
- Mould Resistance: CUAP 2002-01-25 - Pass
- Recoverability and Thickness (EN 823) - Pass
- Recyclable
- Recycled Content – 20%
- Sound Reduction - $R_w = 40\text{dB}$
- Specific Heat Capacity - $1800 \text{ Jkg}^{-1}\text{K}^{-1}$
- Thermal Conductivity - $0.038 \text{ Wm}^{-1}\text{K}^{-1}$
- Vapour Resistivity - $9 \text{ MN}\cdot\text{s}\cdot\text{g}^{-1}\text{m}^{-1}$
- Water Absorption (@100% RH) – 30% w/w

Climate Impact

	Cradle to Gate	Product Lifecycle	Product Carbon Footprint
Standard	EN15804	EN15804	*PAS 2050
Stage	A1-A3	A1-C4	60 year service life
Units	0.06 kg CO _{2e}	1.09 kg CO _{2e}	0.50 kg CO _{2e}

*Greenhouse gas emission calculated by Eden Renewable Innovations Ltd in accordance with PAS 2050, self declared

**Functional unit: 1 m² R 1m²K/W

Acoustic Absorption

Thickness	Weighted Sound Absorption Rating α_w	NRC	Class
(mm)	EN ISO 11654:1997	EN ISO 11654:1997	ASTM C 423-01
50	0.65	0.7	C
75	0.85	0.85	B
100	1	1.05	A
140	1	1	A

Sizes

- **Thicknesses (mm)** tolerance +/- 5mm – 50, 75, 100, 140
- **Widths (mm)** – 370 & 570
- **Slab Length (mm)** – 1200

R-Values

Thickness mm (tolerance +/- 5mm)	Thermal Resistance Km ² W
50	1.32
75	1.97
100	2.63
150	3.95
200	5.26
250	6.18
300	7.42

Installation and Handling

Thermafleece CosyWool is non-hazardous and can be handled without protective clothing, although we recommend you wear PPE in spaces such as lofts.

Protect the insulation from prolonged exposure to sunlight when unpacked and avoid wetting, store under cover and clear of the ground.

If the insulation gets wet during storage or as a result of flooding in service, remove the affected insulation and replace with new.

When installed in walls and floors, spaces filled with CosyWool should be considered as concealed voids for the purposes of fire risk and cavity barriers installed as appropriate. Thermafleece CosyWool is not suitable for use as a cavity barrier.

For cutting information visit the Thermafleece CosyWool Slab product page on the website or take a look at the video on [YouTube](#).

Where to Buy

Our products are available through a wide network of merchants and distributors. To find out more visit our web site www.thermafleece.com or call us on 01768 486285.

